

Quartz 63 Micron(T) / Kuvars 63 mikron (T)

CHEMICAL ANALYSIS

<u>PARAMETER / PARAMETRE</u>	<u>RESULT / SONUÇ</u>
SiO ₂	98,5 % Min
K ₂ O	0,1 % Max
Na ₂ O	0,1 % Max
Fe ₂ O ₃	0,06 % Max
TiO ₂	0,04 % Max
Al ₂ O ₃	0,6 % Max

PARTICLE SIZE DISTRUBITION				
Elek Analizi Sieve Residue			Malvern Masterizer (2000)	
Tolerans	Elek Boyutu		D 50	15±4µ
%	Mesh	Mm	above 63µ	Max 5%
5,0 max	230	+0,063	under 5µ	Max 20%
Nem Humidity	0,03% (Max)			